

# MIDTOWN

## RECOMMENDED AREAS OF USE

With regard to the durability of the bisque and glaze, this material is suitable for:

- All vertical applications - residential and commercial
- All interior walls
- Fireplace surround and firebox
- All exterior wall applications including building facades, swimming pools, fountains and outdoor kitchens, including regions that experience extreme weather conditions, subject to the method of installation



2 1/2" x 4 1/4"  
2 1/2" x 9"

## INSTALLATION AND MAINTENANCE

- Please refer to the TCNA handbook for installation method <http://www.tcnatile.com/>
- Always inspect material prior to installation, for color, shade, size, mounting and any other deciding factors as installed material cannot be accepted for return or credit. Use signifies acceptance.
- Recommended Grout Joint: 3/16" or greater
- Material can be cleaned with any mild nonabrasive household cleaning product due to the chemical resistant nature of the glaze.

## TECHNICAL DATA

- Japanese Porcelain – fired at approx. 2300 degrees Fahrenheit
- Chemical Resistant
- Frost Proof – subject to method of installation
- Water absorbency
  - Bisque less than 1%
  - Glazed surface 0%
- TCNA – MOH's Scale Rating 7
- TCNA – DCOF Avg. rating not applicable
- 2 1/2" x 4 1/4":
  - Loose pcs. – 13 pcs. = 1 sq. ft. / 104 pcs. = 8 sq. ft. per box
  - Weight – 5 lbs. per sq. ft. / 41 lbs. per box
  - Thickness: 9/16"
- 2 1/2" x 9":
  - Loose pcs. – 6 pcs. = 1 sq. ft. / 60 pcs. = 10 sq. ft. per box
  - Weight – 4.9 lbs. per sq. ft. / 51 lbs. per box
  - Thickness – 9/16"
- Pre-consumer recycled content – 52%
- Variations of shade are inherent characteristics of all kiln fired products. To ensure satisfaction, please visually inspect all merchandise prior to installation, as use signifies acceptance.
- We will endeavor to resolve any issues that may arise with material purchased prior to installation.

### PROFILE

EST 1967

# FACINGS

OF AMERICA